

Listing of Claims:

1. (Currently Amended) A fabric wherein the tear strength in the warp cut direction and that in the weft cut direction according to the pendulum method are each from 10 to 50 N, the weight per square-meter is  $50 \text{ g/m}^2$  or less, ~~and~~ the air permeability is  $1.5 \text{ cm}^3/\text{cm}^2\cdot\text{s}$  or less, and the yarn linear density is 30 dtex or less.

2. (Original) The fabric according to claim 1, wherein the bending rigidity according to KES is  $0.025 \text{ gf}\cdot\text{cm}^2/\text{cm}$  or less.

3. (Previously Presented) The fabric according to claim 1, wherein the thickness is 0.07 mm or less.

4. (Previously Presented) The fabric according to claim 2, wherein the thickness is 0.07 mm or less.

5. (Previously Presented) The fabric according to claim 1, wherein the cover factor is from 1600 to 2000.

6. (Previously Presented) The fabric according to claim 2, wherein the cover factor is from 1600 to 2000.

7. (Previously Presented) The fabric according to claim 1, wherein the ratio of the warp density to the weft density is from 0.9 to 1.2.

8. (Previously Presented) The fabric according to claim 2, wherein the ratio of the warp density to the weft density is from 0.9 to 1.2.

9.-10. (Canceled)

11. (Currently Amended) The fabric according to claim 1, ~~characterized by using~~  
comprising a polyamide multifilament wherein ~~the yarn linear density is 30 dtex or less and the~~  
fiber fineness is 1.2 dtex or less.

12. (Currently Amended) The fabric according to claim 2, ~~characterized by using~~  
comprising a polyamide multifilament wherein ~~the yarn linear density is 30 dtex or less and the~~  
fiber fineness is 1.2 dtex or less.

13. (Currently Amended) The fabric according to claim 1, ~~characterized by using~~  
comprising a nylon 6 multifilament wherein ~~the yarn linear density is 30 dtex or less and the~~  
fiber fineness is 1.2 dtex or less.

14. (Currently Amended) The fabric according to claim 2, ~~characterized by using~~  
comprising a nylon 6 multifilament wherein ~~the yarn linear density is 30 dtex or less and the~~  
fiber fineness is 1.2 dtex or less.

15. (Currently Amended) The fabric according to claim 1, ~~which has~~ comprising a rip  
stop weave wherein the lip widths of the longitude and latitude thereof are each 1.5 mm or less.

16. (Currently Amended) The fabric according to claims 2, ~~which has~~ comprising a rip  
stop weave wherein the lip widths of the longitude and latitude thereof are each 1.5 mm or less.

17. (Previously Presented) A process for producing the fabric according to claim 1,  
wherein neither resin finish nor double side calendaring is conducted.

18. (Previously Presented) A process for producing the fabric according to claim 2, wherein neither resin finish nor double side calendaring is conducted.

19. (Previously Presented) The process for producing the fabric according to claim 17, wherein single side calendaring is conducted.

20. (Previously Presented) The process for producing the fabric according to claim 18, wherein single side calendaring is conducted.